



Brazing Turbine Blades with Nickel

Objective To heat an inconel turbine blade in a vacuum to 2000 °F and hold temperature for five minutes for a nickel brazing application.

Material Inconel turbine blades, nickel metering plates, nickel braze


Temperature 2050 °F

Frequency 280 kHz

Equipment ABS Mark 2 with high vacuum option and optical pyrometer for temperature measurement, Ameritherm 20 kW power supply with a remote heat station containing three (3) 0.75 μ F capacitors (for a cumulative capacitance of 0.25 μ F) and a specially-designed induction coil.

Process The Ameritherm ABS Mark 2 with a vacuum level of $<5 \times 10^{-4}$ torr was used for the testing. A specially designed induction coil was used to provide optimal heating (approximately 80% energy efficiency) to the braze joint area. The temperature of the joint area was measured with an optical pyrometer. RF power from the 20kW power supply was applied to the plate for two minutes. As the plate temperature reached 2000 °F, the power was automatically reduced by the pyrometer to maintain the temperature for a five-minute period. A one-minute cool-down Argon quench was used for an overall cycle time of eight minutes.

Results The metering plates were successfully brazed to the turbine blades with nickel within five minutes at 2000 °F. The nickel braze flowed well and the joints were clean. Since only the braze joint area was heated, an additional braze stop-off step was not necessary.



Download and print our Applications Lab Process Sheet (<http://www.ameritherm.com/PDFs/4110038b.pdf>). Answer the questions on the form to help us understand your process and performance requirements. Call with the info on the form to see if you should send us your parts for a free evaluation. If you have questions, call or e-mail us (info@ameritherm.com). We'll be in touch!